

3M Audio Open Reel Tapes, in SI Units

Product Number	Est. Year Introduced	Binder Type	Oxide Ctg Color	Base Material	Base Thickness/ [µm]	Oxide Thickness/ [µm]	Total Thickness/ [µm]	Back Treated	Remanence/ [nWb/m]	Rel Rem Lvl re 3M111/[dB]	Coercivity/ [kA/m]	Retentivity/ [mT]	Special Feature
100	1947	A	black	paper	38.1	17.8	55.9	no	960	-0.6	25.6	55	
101	1948	B	brown	paper	38.1	12.7	50.8	no	1024	0	21.6	90	
102 (111AM)	1953	B	brown	polyester	36.8	12.7	49.5	no	1024	0	21.6	90	
111 (111A)	1948	B	brown	acetate	36.1	12.7	48.8	no	1024	0	21.6	90	
112	1948	B	brown	acetate	36.1	17.8	53.8	no	720	-3.1	13.6	45	tape for Ampex 200A
120 (120A)	1953	B	dark green	acetate	36.1	16.5	52.6	no	1760	4.7	20.8	117	
122 (120AM)	1954	B	dark green	polyester	36.8	16.5	53.3	no	1760	4.7	20.8	117	
131	1958	B	brown	acetate	36.1	10.2	46.2	no	1024	0	21.6	100	
138	1958	B	brown	polyester	36.8	10.2	47	no	1024	0	21.6	100	
139	1958	B	brown	polyester	23.4	10.2	33.5	no	1024	0	21.6	100	
140	1960	B	brown	acetate	36.1	8.9	45	no	1024	0	20.8	110	
141	1960	B	brown	polyester	36.8	8.9	45.7	no	1024	0	20.8	110	
142	1960	B	brown	polyester	23.4	8.9	32.3	no	1024	0	20.8	110	
144	1960	B	brown	polyester	12.7	8.9	21.6	no	1024	0	20.8	110	
150	1954	B	red/brown	polyester	23.4	8.9	32.3	no	1024	0	20.8	110	
151	1964	B	brown	polyester	23.4	10.9	36.8	*	1024	0	21.6	95	*back lubricated tape
152	1964	B	brown	polyester	23.4	10.9	48.8	*	1024	0	21.6	95	*double ctd lube tape
153	1965	D	black	polyester	23.4	10.9	36.3	*	1024	0	21.2	94	*back lubricated tape
154	1972	E	brown	polyester	23.4	6.9	33	*	800	-2.1	22.4	115	*back lubricated tape
156	1972	E	brown	polyester	23.4	6.9	33	*	800	-2.1	22.4	115	*back lubricated tape
157	1973	E	brown	polyester	19.1	9.7	31.2	*	1024	0	25.6	105	*back lubricated tape
158	1973	E	brown	polyester	23.4	6.9	33	*	752	-2.7	25.6	105	*back lubricated tape
175	1965	C	black	polyester	36.1	12.7	48.8	no	1152	1	22	90	
176 (211, 228)	1972	E	brown	polyester	36.1	10.2	46.2	no	1024	0	26	103	
177 (212, 229)	1972	E	brown	polyester	23.4	10.2	33.5	no	1024	0	26	103	
178 (213)	1972	E	brown	polyester	12.7	10.2	22.9	no	1024	0	26	103	
179 (214)	1972	E	brown	polyester	10.9	6.1	17	no	624	-4.3	26	103	
186	1989	L	brown	polyester	37.1	9.1	46.2	no	1088	0.5	29.2	119	
190	1954	B	red/brown	acetate	24.1	8.9	33	no	1024	0	20.8	110	
200	1957	B	red/brown	polyester	12.7	8.9	21.6	no	1024	0	20.8	110	
201	1962	C	black	acetate	36.1	13	49	no	1024	0	25.2	79	
202	1962	C	black	polyester	36.1	13	49	no	1024	0	25.2	79	
203	1962	C	black	polyester	23.4	13	36.3	no	1024	0	25.2	79	
206	1969	D	black	polyester	36.1	14.2	52.8	yes	1488	3.2	25.6	105	
207	1969	D	black	polyester	21.6	14.2	38.4	yes	1488	3.2	25.6	105	
208	1971	D	black	polyester	36.1	10.2	48.3	yes	1024	0	26.4	100	
209	1971	D	black	polyester	23.4	10.2	35.6	yes	1024	0	26.4	100	
217	1982	H	brown	polyester	14.2	8.6	24.9	*	1200	1.4	28.8	140	*back lubricated tape
219	1985	H	brown	polyester	20.1	9.7	31.8	*	1200	1.4	28.8	125	*back lubricated tape
226	1979	H	brown	polyester	33	14.2	49.3	yes	2000	5.8	28.8	140	
227	1980	H	brown	polyester	20.1	14.2	36.3	yes	2000	5.8	28.8	140	
250	1974	F	brown	polyester	33	17.3	52.3	yes	2080	6.2	30.4	120	
265	1977	K	brown	polyester	20.1	3.8	26.4	yes	512	-6	56	135	digital tape
275	1984	L	dark brown	polyester	20.1	4.8	26.4	yes	720	-3.1	56.8	140	digital tape
282	1960	B	red/brn,blk/brn	polyester	36.1	9.9	47	no	1024	0	20.8	103	mag layer overcoat
283	1960	B	red/brown	polyester	23.4	9.9	34.3	no	1024	0	20.8	103	mag layer overcoat
290	1964	C	black	polyester	12.7	4.3	17	no	400	-8.2	21.2	90	
294	1965	C	black	polyester	15.2	10.9	26.2	no	1024	0	21.2	94	
295	1974	E	brown	polyester	10.9	4.6	17.3	yes	576	-5	25.2	126	logging tape
296	1974	E	brown	polyester	21.6	4.6	27.9	yes	576	-5	25.2	126	logging tape
311	1960	B	brown	pvc	36.1	9.7	45.7	no	1008	-0.1	20.8	105	
806	1986	H	brown	polyester	36.1	10.2	48.3	yes	1440	3	29.6	140	
807	1986	H	brown	polyester	23.4	10.2	35.6	yes	1440	3	29.6	140	
808	1986	H	brown	polyester	37.1	8.1	47.2	yes	1072	0.4	28.8	132	
809	1986	H	brown	polyester	23.4	8.1	33.5	yes	1072	0.4	28.8	132	

3M Audio Open Reel Tapes, in SI Units

Product Number	Est. Year Introduced	Binder Type	Oxide Ctg Color	Base Material	Base Thickness/ [µm]	Oxide Thickness/ [µm]	Total Thickness/ [µm]	Back Treated	Remanence/ [nWb/m]	Rel Rem Lvl re 3M111/[dB]	Coercivity/ [kA/m]	Retentivity/ [mT]	Special Feature
908	1993	I	brown	polyester	35.1	9.1	46.2	yes	1440	3	29.2	160	
966/986	1992	I	brown	polyester	35.1	12.4	49.5	yes	2000	5.8	29.2	160	
967	1992	I	brown	polyester	23.4	12.4	37.8	yes	2000	5.8	29.2	160	
996	1990	I	brown	polyester	36.1	16	54.1	yes	2720	8.5	28.8	170	
8135	1972	E	brown	polyester	10.9	5.1	17.8	yes	608	-4.5	25.2	125	logging tape
8136	1972	E	brown	polyester	21.6	5.1	28.4	yes	608	-4.5	25.2	125	logging tape
8206	1977	J	dark brown	polyester	20.1	5.1	26.7	yes	544	-5.5	27.6	105	logging tape
8207	1977	J	dark brown	polyester	10.9	5.1	17.5	yes	544	-5.5	27.6	105	logging tape
8265	1981	K	brown	polyester	23.4	4.1	29	yes	512	-6	52	125	digital tape
8614	1978	J	dark brown	polyester	20.1	5.1	25.1	no	544	-5.5	27.6	105	logging tape
Classic DP	1975	H	brown	polyester	10.7	12.2	24.9	yes	1440	3	28	120	
Classic LP	1975	H	brown	polyester	20.3	12.2	34.5	yes	1440	3	28	120	
Classic SP	1975	H	brown	polyester	36.1	12.2	50.3	yes	1440	3	28	120	
Master	1978	H	brown	polyester	20.3	12.2	34.5	yes	1440	3	28	120	
Master XS	1980	H	brown	polyester	20.1	14.2	36.3	yes	2000	5.8	28.8	140	
rev.2-SI scotch	2011-04-24												